Environma Lyssy L100-5000 Stion Analysing

nentation

ency Ultraviolet

Gas Production owdered Metals

d Environments

s Manufacturing

ecarbon Refining

Food Packaging

s ■ Glove Boxes

on Beam ■ R & D

■ Fermentation

d Environments

Manufacturing

ssel Blanketing

tion Analysing

ncy Ultraviolet

Gas Production

vdered Metals

Environments

anufacturing el Blanketing

S Production

ered Metals

rironments

ufacturing

ıfacturing

Analysing

; Production



Manometric gas permeability tester Versatile and short testing time

The manometric gas permeability tester is an extremely versatile instrument that can measure the permeability of practically any common gas or gas mixture through films and foils.



Typical gases measured include air, oxygen, nitrogen, carbon dioxide, hydrogen and helium.

With the manometric principle, this instrument utilises one of the oldest and most recognised gas permeability testing methods: pressure change via gas transmission through films.

With two measuring chambers, ease of operation through the alpha-numeric keyboard and digital display, the L100-5000 has the versatility of measuring permeation of almost any gas, both for advanced laboratory research as well as for quality control in a production setting.

The L100-5000 tester is capable of measuring within a broad range of low and high permeabilities, and can thus be used to test a variety of materials. Test results are exposed directly in cc/m²/day, and are documented using the built-in printer.

Features & Benefits

- Automatic equilibrium detection
- Flexibility in the use of the two measuring chambers
- Suitable for all permanent, non-corrosive gases
- Fast and accurate test result
- Compact instrument
- Built-in printer
- Test results expressed directly in cc/m²/day
- Easy to use operator interface

- Simplicity in operation due to the high degree of automation - the quality of tests performed is less operator dependent
- Extremely broad testing range, covering low and high permeability
- High repeatability of testing results
- Complete traceability in test documentation, data logging and error reports
- Easy to use test sample holders
- Low degree of maintenance


Sample cards

The preparation of samples for the L100-5000 is fast and easy. No grease or glue is required for a tight seal around the sample in the chamber.

The test sample is affixed to the self-adhesive sample card, which is inserted into one of the test chambers, separating the upper and lower chamber.



Example of measuring cycle L100-5000



Technical Specifications

General description

Dimensions 480H x 400W x 486D cm

Weight Approx. 28 Kg

Measuring range 1 - 10,000 cc/m²/day as standard

Measuring principle Manometric, first principle

230 VAC or 115/100 VAC Voltage

5 - 75°C. External water thermostat required for temperature control. Measuring temp. range

ASTM D1434-82, DIN 53380-2, ISO 15105-1, JIS K7126 Conforms to the

following standards 2-step rotary vacuum pump.

Required accessory for operating

Measuring

Equilibrium detector 0 - 99.99% Reproducibility Better than 2.5% Calibration Using test standard

Sample requirements

Measuring area

Low permeability samples - 50 cm² High permeability samples - 2.5 cm²

Sample Thickness Up to 5 mm Min. sample size 10 x 10 cm

Data logging

Prepared for RS232 Serial output to PC Data transfer

or external printer.

Printer Built-in 80mm thermal printer

User Interface

Keyboard Alpha-numeric

Display Vacuum fluorescent display

Operational Environment

Ambient temperature 5-40°C

Ambient humidity 10 - 90% R.H. (non-condensing)

Accurate and versatile

The L100-5000 can be used to test a variety of products, including packaging films for food and tobacco; material for contact lenses: coated paper; and complex protection membranes.

palloured ontact Lens I inealing ■ Ve

amics Combu

Oxygen Defici

s
High Purity

Alloys and P

lity ■ Controlle

I ■ Contact Len

keting ■ Hydro

on Analysing **•**

ass/Fibre Optio

uction ■ Electro

Ndered Metals

ity ■ Controlle

■ Contact Lens

Annealing ■ Ve

ramics Combus

Oxygen Deficie

■ High Purity

Alloys and Pov

■ Controlled |

ontact Lens M

aling ■ Vesse

s Combustic

n Deficiency

h Purity Gas

and Powd

ntrolled Env

als 🔳 Fern

■ Vessel E

ombustion

Deficiency

Purity Gas

The L100-5000 tester is capable of measuring both high and low permeability with a broad measuring range from 1-10,000 cc/m²/day. The two chambers of the L100-5000 makes the instrument very versatile, providing the following range of testing possibilities:


- Different samples, same gas
- Same sample, different gases
- Same samples and gas at different temperatures

(two external water thermostats required)

Measuring temperature

The L100-5000 does not have internal temperature control. Since most test standards recommend measuring at 23°C, an external cooling thermostat is required. However, measurements can still be done without the external cooler at 5-10° above the ambient temperature. If the two measuring chambers should be operated at two different temperatures, two external coolers are required.

Measuring principle of L100-5000



Systech Instruments Ltd (UK) 17 Thame Park Business Centre,

Wenman Road, Thame, Oxfordshire OX9 3XA Tel: +44 (0)1844 216838 Fax: +44 (0)1844 217220 E-mail: advice@systech.co.uk

www.systechillinois.com

Illinois Instruments, Inc (U.S)

2401 Hiller Ridge Road Johnsburg, Illinois 60051

U.S.A

Tel: +1 815 344 6212 Fax: +1 815 344 6332

E-mail: sales@illinoisinstruments.com www.svstechillinois.com

Illinois Instruments (Thailand)

6th fl Nopnarong Bldg No7 Ladprao23, Jatujak, Bangkok 10900 **Thailand**

Tel: +66 (0)2938 0798 Fax: +66 (0)2938 1058

E-mail: mai@illinoisinstruments.com www.systechillinois.com

Systech Illinois (China)

www.svstechillinois.cn

Room 519, No.3 FuCheng Building No. 900 Quyang Rd, Hongkou district, Shanghai, China 200434 Tel: +86 21 65533022 Fax: +86 21 65539651 Email: info@systechillinois.cn

Systech Illinois reserve the right to change specifications without notice. 01/2011